

試驗報告



報告編號：HB-18-05692

C-18-21713

頁數：1 OF 1

報告日期：107年08月28日

委託單位：羅威科技股份有限公司
 樣品名稱：生物水泥
 送驗人員：羅威科技股份有限公司(林宥緒)
 收件日期：107年07月26日
 試驗日期：107年07月31日~107年08月28日
 備註：1. 以上資料由顧客提供(收件及試驗日期除外)
 2. 除非另有說明，此報告結果僅對測試之樣品負責
 未經本公司事先書面同意，此報告不可部分複製

=====
 試驗結果：

試驗項目	試驗方法	試驗結果	
		標準組	試驗組
抗壓強度(kgf/cm ²) 28天	參考 ASTM C109/C109M-16a	標準組	294.3
		試驗組	329.5

註：1. 配比(重量比)：標準組=水泥(台泥 I 泥)：標準砂：水=1：3：0.52
 試驗組=水泥(台泥 I 泥)：標準砂：水：生物水泥=1：3：0.52：0.02

生物水泥添加量：為水泥用量之 2%


水泥(台泥 I 泥)及標準砂由實驗室提供

2. 拌合方式：依照 ASTM C305-06 拌合壩料之步驟

3. 養護方式：23±2°C 飽和石灰水中養護。

4. 本試驗之樣品不在 TAF 認可範圍內，故無法出具 TAF 標誌之報告。

規範要求值僅供參考，合格之判定以委託單位實際要求為準。


 報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.